Current Industrial Composites
Sheeting · Tubes · Rods · Fabricated Parts · Epoxy · Phenolic

TECHNICAL DATA SHEET

X

Mil-I-24768/12, PBM

REQUIREMENT	
Minimum Dielectric Strength	325v/mil
Compressive Strength (Axial)	10000 psi
Minimum Density	1.10g/cm^3
Maximum Water Absorption	8%
Tensile Strength	8500 psi
Flexural Strength	N/A
Dissipation Factor	N/A
Permittivity @ 1 MHz	N/A
Maximum Operating Temperature	120°C