Current Industrial Composites
Sheeting · Tubes · Rods · Fabricated Parts · Epoxy · Phenolic

TECHNICAL DATA SHEET

LE

Mil-I-24768/13, FBE

REQUIREMENT	
Minimum Dielectric Strength	140v/mil
Compressive Strength (Axial)	13000 psi
Minimum Density	1.12g/cm^3
Maximum Water Absorption	7.5%
Tensile Strength	7000 psi
Flexural Strength	N/A
Dissipation Factor	N/A
Permittivity @ 1 MHz	N/A
Maximum Operating Temperature	125°C